STAR TEAK (PROTECTIVE) SEALER

PROTECTIVE OIL FOR TEAK AND TROPICAL WOODS

Solvent based protective teak oil sealer specifically formulated for the treatment and maintenance of teak and other precious woods, providing suitable protection from the sun and from weather exposure in marine environment. Particularly used on boat decks made of teak or similar woods. STAR TEAK SEALER is part of the Star Teak Line, also including Star Teak Brightener and Star Teak Cleaner.

TECHNICAL CHARACTERISTICS		APPLICATION DATA	
Paint type	One component	Application:	Thinning:
Binder type (Sol.A)	Alkyd modified	Brush-Roller	Ready for use
Code & colour (Sol.B)	6D4892.Clear Ambered		(add Thinner 107 if required)
Specific gravity kg/lt (±0.05)	0,850	Dust dry	1-2 h (20°C)
Solids content (volume) ±2	13%	Recoat time	1-2 h (20°C)
Viscosity Ford ø 4 at 20°C ±2	15-18 "	Application temperature	Between +10°C and +40°C
Shelf life (+10+30°C)	18 months in airtight cans	Relevant humidity	Lower than 80%
Packaging Lt	1	Dry film thickness advised	according to absorption
		Theoret. coverage m2/Lt	9-13

SURFACE PREPARATION AND APPLICATION

New Wood. The surface should be clean, dry and sandpapered. Remove dust. Apply a first coat of STAR TEAK SEALER by brush or by a soft pad evenly all over the surface and let dry for 24 hours. In the caase of particular dry wood, repeat application few times allowing 1-2 hours between applications.

Old Wood. Wet the wood surface with fresh water and apply STAR TEAK CLEANER evenly all over the surface and let it stand for 5-10 minutes. Any trace of grease or dirt should be removed using a nylon brush. Rinse with plenty of fresh water. In case it would be necessary to brighten the shade of wood or any blackish shade caused by the natural ageing of wood, then apply on the wet SURFACE STAR TEAK BRIGHTENER by brush. Use a nylon brush to brush off the surface, rinse with plenty of water and let dry for 24 hours. In case of difficult stains repeat the application with Star Teak Brightener. Apply STAR TEAK SEALER by brush or by a soft pad and let dry for 24 hours. In the case of particular dry wood, repeat application few times allowing 1-2 hours between applications. When hot temperatures are present it can be necessary to repeat the application specially on those areas where ther wood is more worn out or dull.

NB: This product is part of the Skipper's Line of Marine Coatings. For further application details please also see the "Indicative Coating Systems information" available on demand for Wood, Steel, Aluminium and Fibreglass boats. When in doubt contact for advise.

SAFETY PRECAUTIONS

Before starting the application please read carefully all the safety precautions stated on the label of each can. A Safety Data Sheet of the product is also available on request. For further information please do not hesitate to contact our Technical staff. www.aemmecolori.it

NOTE

The above information is given to the best of our knowledge but since the conditions of use of our products are beyond our control, no warranty is given or to be implied in respect of such information. Our technical staff can be contacted to study customer's specific requirements involving our products in order to enable their most effective use. Dilution rates and drying times are to be considered only indicative, mainly related to a temperature of 20°C (68°F), and may be subject to changes according to prevailing temperature, in presence of particular weather conditions or due to application procedures that may be effective at time of application. **Product Data Sheet last revised on: 01.02.11**



AEMME COLORI SRL · Paint industry since 1947 Via Patta 12 · 24020 Ranica-Italy · Tel.+39-035-513373 Fax +39-035-513211 info@aemmecolori.it

