

Codice: 6Z0000

Superwind Lucida

ONE-COMPONENT TRADITIONAL GLOSS VARNISH



Traditional urethane varnish with excellent filling power, brilliancy and resistance in the marine environment. Applied on wooden boats, furniture, handrails, external frames, etc. to obtain a classic gloss finish.

Technical Characteristics

| | |
|---------------------------------------|----------------------------|
| Paint Type | One component |
| Binder type A | Urethane modified |
| Specific gravity kg/lt (±0,05) | 0.930 |
| Solids content (volume) ±2 | 57% |
| Shelf life (+10+30°C) | 18 months in airtight cans |
| Viscosity Ford Ø4 | 120-130 |

Application Data

| | |
|-----------------------------------|---------------------------|
| Application | Brush-Roller-Spray |
| Brush-Roller | 10-15% Thinner 107 or 109 |
| Spray | 10-20% Thinner 900 |
| Touch dry | 6-8 h |
| Recoat time | 24 h |
| Application temperature | Between +10 C and +40 C |
| Relevant humidity | Less than 80% |
| Dry film thickness advised | 40 microns per coat |
| Theoret. coverage m2/Lt | 12-13 |

SURFACE PREPARATION AND APPLICATION PROCEDURE

Bare Wood.

The surface should be clean and dry, sandpapered and dusted off. Apply a first coat of SUPERWIND onto bare wood, highly diluted up to 50-70% (depending on wood absorption) in order to allow the varnish to sink into the wood substrate. As a clear primer alternative, one coat of POLIGLASS two-component varnish diluted 50-100% (depending on wood absorption) with Thinner 203 can be applied; care should be taken in order to maintain the grain of the wood open so to enable the application of subsequent coats of SUPERWIND LUCIDA varnish. Overcoat then with 4-5 coats of SUPERWIND LUCIDA, allowing the required waiting time between coats.

Previously Varnished Wood.


- If the old paint is in poor conditions, loose or powdery, it should be mechanically removed. Clean the surface well and follow application directions as per bare wood.

- If the old paint is in good condition of adhesion and it only needs a topcoat because it is dull or dirty but with the underneath coatings still well fixed to the substrate (with no cracks or bubbles), clean, degrease and sandpaper with medium-fine abrasive paper and apply 2-3 coats of SUPERWIND LUCIDA varnish, allowing the required waiting time between coats.

Codice: 6Z0000

Superwind Lucida

Colors



Colore: TRASPARENTE

Cod. Colore: 6Z0000

SAFETY PRECAUTIONS

Before starting paint application please carefully read all the safety precautions indicated on the label of each can or in the product safety data sheet available on request. For further information please do not hesitate to contact our technical staff.

NOTES

The above information is given to the best of our current knowledge, however, because the conditions of use of our products are beyond our control, no warranty is given or to be implied in respect of such information. Our technical staff can be contacted to study customer's specific requirements involving our products in order to enable their most effective use. Dilution rates and drying times must be considered only indicative, mainly related to a temperature of 20 ° C (68°F) and may vary according to prevailing temperature, in presence of particular weather conditions or depending on application procedures.